

TECHNICAL DATA SHEET

AV-202-LV MULTIGROUT LV™

HYDROPHILIC POLYURETHANE GROUT

DESCRIPTION

AV-202-LV Multigrout LV™ is the low viscosity version of the original **AV-202® Multigrout**. It is a single component moisture activated MDI/TDI blended polyurethane injection resin designed for sealing active water leaks in cracks or joints in concrete structures. **AV-202-LV** can withstand high water flows as it can absorb up to 8 times its weight in water. **AV-202-LV** is designed to permeate tight cracks or joints and cures flexible, tough and closed-cell with superb adhesive qualities.

APPLICATION

- Various cracks or joints in concrete, or used in conjunction with **AV-215 Resin Rod™** or **AV-219 Fibrotite™** (oakum) systems
- Designed for applications where the flexibility and variability of **AV-202-LV** is desired but better penetration is needed from a lower viscosity chemistry
- Used routinely in manhole sealing and pipe penetrations
- Excellent choice for moving cracks and joints

FEATURES AND BENEFITS

- Low viscosity version of the original **AV-202® Multigrout**
- 100% solids
- Free rise expands 400-600%
- Solvent-free and non-corrosive
- Cures flexible with superb adhesive properties
- Can accept up to 8X its weight in water

GROUTING TECHNIQUES

- Expanded Gasket Placement Technique (EGP)
- Variable Pressure Application Technique (V-PAT)

HOW IT WORKS

AV-202-LV can be applied via two techniques: EGP or V-PAT. The resin reacts to moisture to form a resilient, flexible seal accomplished by three mechanisms: the resin seeks out water in the space and adheres to the surface, then begins to expand forming a tight compressive seal, while the network of compressed grout material within all the cracks forms a mechanical lock.

RATIOS

Preferred ratio is 1:1 (water to resin), however no mixing is required. Pumped as a single component and is effective at a ratio of 10:1 with water.

PACKAGING

Product packaged by weight based on specific gravity.

Drum	Net Wt. 484 lbs. (220 kg)
Pail	Net Wt. 44 lbs. (20 kg)
Gallon	Net Wt. 8 lbs. (3.6 kg)
Cartridge	~10.114 fl. oz. (~ 300 ml)

SHIPPING

- Motor class 55
- Non-hazardous
- Air freight available

PROPERTIES*

UNCURED

Appearance:	Brown resin
Viscosity:	650-800 cP @ 72°F (22°C)
Flash Point:	>200°F (>93°C)
Specific Gravity:	1.078 @ 72°F (22°C) ± 3%
Density:	9.0 lbs/gal (1,078 kg/m ³) ± 3%

CURED

Appearance:	Milky colored, flexible
Tensile Strength:	TBD
Elongation:	TBD

*Laboratory Results

PERFORMANCE

Flush equipment with **AV-208** Technical Grade Acetone™ before and after use to remove moisture and clean equipment. For best results, use between 60°F – 90°F (16°C – 32°C). Performance will be influenced by site conditions. If site temperatures are low, use a heat source to warm to ~72°F (22°C) and apply. Do not use open flame as a heat source. At temperatures of 45°F (7°C), the viscosity of the product can significantly increase, making the miscibility with the reaction water more difficult.

CLEANING PRODUCTS

- **AV-208** Technical Grade Acetone™ (CAS# 67-64-1) – removes moisture from equipment
- **AV-284** Pump Wash™ (Proprietary Blend) – removes uncured resin from pump and hose
- **AV-222** Cleaner™ (Proprietary Blend) – removes cured resin from equipment

STORAGE

Store in temperatures within or near 45°F – 95°F (7°C – 35°C) in a dry atmosphere. Keep container tightly closed when not in use. Packaged under dry nitrogen to keep moisture out and extend shelf life.

Note: storage of opened/partial containers at the lower range of the recommended storage temperature is not advised. The moisture in the air of the head space above a partial container might condensate and causes the grout to premature gel in the container.

SAFETY

Always use OSHA-approved personal protective equipment (PPE). Refer to the SDS for complete safety precautions. The SDS is available by request or via download at avantigrout.com.

NOTICE

The data, information and statements contained herein are believed to be reliable but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. **NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE.** In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.