

## AV-203 Multicat™

Grout-Side Accelerator for Hydrophilic Polyurethane Grout

### Description

AV-203 Multicat™ is a grout-side only accelerator that speeds up the reaction time of the following Avanti's **hydrophilic** polyurethane grouts:

- AV-202® Multigrout
- AV-202-LV Multigrout LV™
- AV-202-NTP Multigrout NTP™
- AV-254 Gelseal™
- AV-315 Microfoam™
- AV-330 Safeguard™
- AV-330-NTP Safeguard NTP™

*Note: Do not use AV-203 with Avanti's hydrophobic polyurethanes or acrylic grouts.*

**Packaging** – product is packaged by net weight except when indicated

- Container - 78 fl. oz. (2.31 L)

### Physical Properties\*

| AV-203 Multicat            |                                      |
|----------------------------|--------------------------------------|
| Appearance                 | Light yellow liquid                  |
| Viscosity (water=1)        | 5-10 cP @ 72°F (22°C)                |
| Flash Point                | >200°F (>93°C)                       |
| Specific Gravity (water=1) | 0.879 @ 72°F (22°C) ± 3%             |
| Density                    | 7.33 lb./gal. ± 3% (0.879 kg/L ± 3%) |

\* Laboratory results

### Performance

**Using AV-203 with WQA certified polyurethanes is not tested and certified by WQA against NSF/ANSI/CAN 61 Drinking Water System Components.** Gently shake or stir container(s) before using. The preferred ratio is from 8:1 to 16:1 (resin to catalyst). For the best results, use AV-203 between 60°F – 90°F (16°C – 32°C). Performance will be influenced by site conditions. If site temperatures are low, use a heat source to warm to ~72°F (22°C) and apply. Do not use open flame as a heat source. AV-203 Multicat may be used at low temperatures and/or high flow water cut-off situations at a maximum of 78 fl. oz. of AV-203 per pail of hydrophilic polyurethane. **When AV-203 is used to slow down high waterflows, it should not be used as a stand-alone solution but in conjunction with any of Avanti's injection grouts.** Refer to each individual grout's Technical Data Sheet for cream and gel times. Do not use AV-203 with Avanti's hydrophobic polyurethanes or acrylic gels.

### Storage

Store in temperatures within or near 45°F – 95°F (7°C – 35°C) in a dry atmosphere. Keep container tightly closed when not in use. Packaged under dry nitrogen to keep moisture out and extend shelf life.

### Safety

Always use OSHA-approved personal protective equipment (PPE). Refer to the product Safety Data Sheet (SDS) for complete safety precautions. The SDS and Mixing Guidelines are available 24/7 at [avantigrout.com](http://avantigrout.com).

**Shipping** – Motor and Air Freight available

- Not regulated under US DOT Regulations

### Notice

The data, information and statements contained herein are believed to be reliable but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. **NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE.** In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.

Rev. 03.2025