

TECHNICAL DATA SHEET

AV-248-HV FLEXSEAL HV™

HYDROPHOBIC POLYURETHANE GROUT

DESCRIPTION

AV-248-HV Flexseal HV™ is a moisture activated, MDI-based polyurethane resin whose reaction is catalyzed by mixing **AV-249-HV Cat-HV™** with AV-248-HV. **AV-248-HV** is injected as a single component and designed for sealing active and potential water leaks in cracks or small annular spaced when flexibility is needed. **AV-248-HV** withstands wet/dry cycles. **AV-248-HV** cures resilient, impermeable, and flexible.

APPLICATION

- For use above or below grade in humid or arid atmospheres
- Fills various cracks and pipe penetrations
- Stops leaks in concrete structures
- Designed for tunnels, mines, dams, reservoirs, block walls and structures that may shift

FEATURES AND BENEFITS

- Free rise expands 400% – 600%
- Solvent-free system
- Controllable reaction time by adjusting **AV-249-HV** Cat-HV volume
- Withstands wet/dry cycles
- Unique hydrophobic that cures flexible and closed cell

GROUTING TECHNIQUES

- Expanded Gasket Placement Technique (EGP)
- Variable Pressure Application Technique (V-PAT) – Crack Injection

HOW IT WORKS

AV-248-HV Flexseal HV uncured resin must be injected into a confined space. Fill the space at least halfway with unreacted resin. The resin will react with moisture to form a resilient seal accomplished by three mechanisms: the resin seeks out water in the space and adheres to the surface, then begins to expand in the confined space to form a tight, high density compression seal, while the network of compressed grout material within all the cracks/joints forms a mechanical lock.

CATALYST

- **AV-249-HV** Cat-HV – 25 fl. oz. (1.44 lbs., 0.65 kg)

PACKAGING

Product packaged by weight based on specific gravity.

Drum	Net Wt. 484 lbs. (220 kg)
Pail	Net Wt. 44 lbs. (20 kg)
Gallon	Net Wt. 8 lbs. (3.6 kg)

SHIPPING

- Motor Class 55
- Non-Hazardous
- Air freight available

CLEANING PRODUCTS

- **AV-208** Technical Grade Acetone™ (CAS# 67-64-1) – removes moisture from equipment
- **AV-284** Pump Wash™ (Proprietary Blend) – removes uncured resin from pump and hose
- **AV-222** Cleaner™ (Proprietary Blend) – removes cured resin from equipment

PROPERTIES*

AV-248-HV – UNCURED

Appearance:	Clear liquid
Viscosity:	1,200 cP ± 200 @ 72°F (22°C)
Flash Point:	>225°F (>107°C)
Solids:	90 – 98%
Specific Gravity:	1.04 @ 72°F (22°C) ±3%
Density:	8.68 lbs./gal (1,040 kg/m³) ±3%

AV-248-HV – CURED

Appearance:	Milky white, flexible
Tensile Strength:	800 – 1200 kPa (116-174 psi)
Elongation:	200 – 250%
Shrinkage:	<4%
Toxicity:	Non-toxic

AV-249-HV Cat-HV

Appearance:	Light yellow, clear liquid
Viscosity:	22 cP @ 72°F (22°C)
Flash Point:	>255°F (>124°C)

*Laboratory Results

MIX PROCEDURE

Typically, one container of **AV-249-HV** Cat-HV is used per 5-gallon container of **AV-248-HV** Flexseal HV. Depending on the desired reaction time, **AV-249-HV** may be doubled. Mix thoroughly, but slowly, to avoid creating bubbles in the solution. Perform the standard cup test with site water to determine the desired reaction time.

PERFORMANCE

Flush equipment with AV-208 before and after use to remove moisture and clean equipment. Performance will be influenced by site conditions. If site temperatures are low, heat the product to recommended operating temperatures of 60°F – 90°F (16°C – 32°C) and/or increase catalyst amount by 1% – 2%. Do not exceed more than 50 fl. oz. (1.5 L) of **AV-249-HV** Cat-HV per 5-gallon container of the **AV-248-HV** Flexseal HV resin. Do not use open flame as a heat source. Excess amounts of **AV-249-HV** may adversely affect performance. Because catalyzed resin will react to moisture from the air, use product soon after mixing for best results.

STORAGE

Store in temperatures within or near 45°F – 95°F (7°C – 35°C) in a dry atmosphere. Keep container tightly closed when not in use. Packaged under dry nitrogen to keep moisture out and extend shelf life.

SAFETY

Always use OSHA-approved personal protective equipment (PPE). Refer to the SDS for complete safety precautions. The SDS is available by request or via download at avantigrout.com.

NOTICE

The data, information and statements contained herein are believed to be reliable but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. **NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE.** In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.