

TECHNICAL DATA SHEET

AV-275 SOILGROUT™

HYDROPHOBIC POLYURETHANE GROUT

DESCRIPTION

AV-275 Soilgrout™ is a low viscosity, moisture-activated, MDI-based polyurethane resin whose chemical reaction is catalyzed by mixing **AV-276 Soilcat™** with **AV-275**. Injected as a single component, **AV-275** is designed to react quickly with moisture to bind together and waterproof loose granular soils and fill voids. **AV-275** forms a dense, impermeable rigid soil/grout matrix, withstands wet/dry cycles, and permeates well.

APPLICATION

- Fills voids on the exterior of below-grade structures
- Stops high flows in below-grade structures
- Stabilizes soil to prevent soil erosion, sink holes, sinking foundations, and infiltration of water and silty soils

FEATURES AND BENEFITS

- **NSF/ANSI/CAN 61 Drinking Water Systems Component Certified**
- Low viscosity allows for excellent permeation
- Free rise expands up to 3,000%
- Pumped as a single component (pre-mixed with **AV-276**)
- Controllable reaction time by adjusting **AV-276** volume
- Withstands wet/dry cycles

GROUTING TECHNIQUES

- Curtain Grouting
- Probe Grouting
- Pressure Injection

HOW IT WORKS

AV-275 Soilgrout uncured resin must be injected into a confined space. Fill the space at least halfway with unreacted resin. The resin will react with moisture to form a resilient seal accomplished by three mechanisms: the resin seeks out water in the space and adheres to the surface, then begins to expand in the confined space to form a tight, high density compression seal, while the network of compressed grout material within all the cracks/joints forms a mechanical lock.

CATALYST

- **AV-276 Soilcat** – 32 fl. oz. container (approx. 1.88 lbs. (0.84 kg))

PACKAGING - Product packaged by weight based on specific gravity.

Drum	Net Wt. 484 lbs. (220 kg)	
Pail	Net Wt. 44 lbs. (20 kg)	
Dual Cartridge	AV-275 – 25.3 fl. oz. (750 ml)	AV-276 – 2.5 fl. oz. (75 ml)

SHIPPING

- Motor Class 55
- Non-Hazardous
- Air freight available

CLEANING PRODUCTS

- **AV-208** Technical Grade Acetone™ (CAS# 67-64-1) – removes moisture from equipment
- **AV-284** Pump Wash™ (Proprietary Blend) – removes uncured resin from pump and hose
- **AV-222** Cleaner™ (Proprietary Blend) – removes cured resin from equipment

STORAGE

Store between 45°F – 95°F (7°C – 35°C) in a dry atmosphere. Keep lid tightly closed when not in use. Packaged under dry nitrogen to keep moisture out and extend shelf life.

MIX PROCEDURE

Typically, one container of **AV-276** is used per pail of **AV-275**. Depending on desired reaction time, **AV-276** may be doubled. Mix thoroughly and slowly to avoid creating bubbles in the solution. Perform a standard cup test with site water to determine desired reaction time.

PROPERTIES*

AV-275 – UNCURED

Appearance:	Black/brown liquid
Corrosiveness:	Non-Corrosive
Solids:	100%
Viscosity:	30-55 cP @ 77°F (25°C) ASTM D-4889
Flash Point:	309.2°F (154°C)
Specific Gravity:	1.114 @ 72°F (22°C) ± 3%
Density:	9.3 lb./gallon ± 3% 1,114 kg/m ³ ± 3%

AV-275 – CURED*†

Tensile Strength:	758.423 kPa (110 psi) ± 3%
Density:	1,074 kg/m ³
Bending Strength:	213 psi
Bond Strength:	99 psi
Shrinkage:	0%
Toxicity:	Non-Toxic

† Cured properties vary depending on application and field conditions.

AV-276

Appearance:	Light yellow liquid
Viscosity:	15-32 cP @ 70°F (21°C)
Flash Point:	>200° F (93.3°C)

*Laboratory Results

Gel (Cure) Times for AV-275 Soilgrout (Min:Sec)				
Temperature	Catalyst			
	Half Catalyst	Full Catalyst	Double Catalyst	
40°F / 4°C	8:17	4:30	2:55	
50°F / 10 C	7:05	4:08	2:27	
60°F / 15°C	4:30	3:18	2:10	
70°F / 21°C	3:40	2:08	1:00	

PERFORMANCE

Flush equipment with **AV-208** before and after use to remove moisture and clean equipment. Performance will be influenced by site conditions. If site temperatures are low, heat the product to recommended operating temperatures of 60°F – 90°F (16°C – 32°C) and/or increase catalyst amount by 1% – 2%. Do not exceed more than 64 fl. oz. of **AV-276** Soilcat per pail of **AV-275** Soilgrout. Do not use open flame as a heat source. Excess amounts of **AV-276** may adversely affect performance. Because catalyzed resin will react to moisture from the air, use product soon after mixing for best results.

SAFETY

Always use OSHA-approved personal protective equipment (PPE). Refer to the SDS for complete safety precautions. The SDS is available by request or via online download at avantigrout.com.

NOTICE

The data, information and statements contained herein are believed to be reliable but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. **NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE.** In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.



AV-275 Soilgrout™ is tested and certified by WQA against NSF/ANSI/CAN 61 Drinking Water System Components

For product use restrictions visit www.wqa.org