



**TECHNICAL DATA SHEET**

**AV-100<sup>®</sup> CHEMICAL GROUT**

**GRANULES / LIQUID CHEMICALLY REACTIVE GEL**

**DESCRIPTION**

**AV-100** Chemical Grout is an ultra-low viscosity chemically reactive gel available as either granules or liquid. Having the same viscosity as water, **AV-100** can permeate anywhere water can travel and cures within a controllable time frame anywhere from 5 seconds to ±10 hours. Once it cures, it creates an effective, long-lasting water barrier while providing superb soil stabilization.

**APPLICATION**

- Stops water infiltration into manholes, sanitary and storm sewer mainlines, joints, laterals, tunnels, mines, and various other geotechnical applications and underground structures by stabilizing external substrate
- Ground modification/slope stability for prevention of landslides, erosion, or any place where site conditions or project requirements dictate modification of the existing soil properties

**FEATURES AND BENEFITS**

- Thinnest product on the market
- Can be injected through remote packer equipment
- Controllable reaction times from seconds to hours
- Will not undergo syneresis
- Half-life of 362 years for 20% grout concentration, as determined by U.S. Dept. of Energy
- No suspended solids
- Higher strength compared to acrylates
- Greater longevity compared to silicates
- Available in granular or liquid form

**GROUTING TECHNIQUES**

- Tube-a-Manchette (TAM) Grouting
- Probe Grouting
- Curtain Grouting
- Remote Packer

**HOW IT WORKS**

**AV-100** is injected using a stainless steel, dual-component pump from two containers (see mix procedure). Injecting a 1:1 ratio into the soil or external substrate will produce a strong, impermeable gel obtained via a copolymerization reaction. Additives are available to modify the reactions and cured gel characteristics.

**OPTIONAL ADDITIVES**

- **AV-257** Icoset™ – increases strength (add to grout tank)
- **KFe** (Potassium Ferricyanide) – extends gel time (add to grout tank)
- **AV-105** Gel Guard™ – reduces freezing point (add equal amounts to both tanks)
- **Dyes** – used extensively for tracking grout flow

**PACKAGING**

	Net Wt.	Volume
Bag (Granules)	30 lbs. (13.6 kg)	—
	50lbs. (22.6 kg)	
Tote (Liquid)	2300 lbs. (1,043 kg)	258 – 265 gal. (976 – 1,003 L)
Drum (Liquid)	130 lbs. (58.9 kg)	14.6 – 15 gal.
		(55.2 – 56.7 L)

**SHIPPING**

- Motor class 77.5
- Hazard class 6.1
- Motor freight available
- Air freight available

**PROPERTIES\***

<b>UNCURED (solid)</b>	
Appearance:	White granules
Specific Gravity:	1.122 @ 68°F (20°C) ±3%
Bulk Density:	71.79 lbs./ft <sup>3</sup> ± 3% (1150 kg/m <sup>3</sup> ± 3%)
Toxicological:	See SDS
<b>UNCURED (liquid)</b>	
Appearance:	Clear water-white liquid
Viscosity:	1 – 2 cP @ 72°F (22°C) in solution
Specific Gravity:	1.03 @ 77°F (25°C) ± 3%
Density:	8.66 lbs./gal ± 3% (1.038 kg/L ± 3%)
Toxicological:	See SDS
<b>CURED</b>	
Appearance:	Clear gel mass/translucent
Hydraulic Conductivity:	< 10 <sup>-8</sup> m/s
Toxicity:	Non-toxic

\*Laboratory Results

**MIX PROCEDURE (See Mixing Instructions)**

Tank A: Add 10 gallons (37.8 L) of water, add one 50 lb. bag (granules) or one liquid drum of **AV-100** to solution, add 0.5 gallons (1.9 L) of **AV-101<sup>®</sup>** Catalyst T+ and fill with water up to 30 gallons. Tank B: Add 10 gallons (37.8 L) of water, add 5 lbs. (2.27 kg) of **AV-102<sup>®</sup>** Catalyst AP, and then bring to 30 gallons with water. Makes a 60 gallon (227 L) batch. Note: Ingredients are only compatible with stainless steel or plastic.

**PERFORMANCE**

Performance will be influenced by site conditions. If site temperatures are low, heat the product to recommended operating temperatures of 60°F – 100°F (16°C – 38°C). Decreasing pH may extend cure time. High minerals/metals content may adversely affect gel time. Refer to **AV-100** Technical Manual for complete product information.

**STORAGE**

Store in temperatures within or near 45°F – 95°F (7°C – 35°C) in a dry atmosphere. Keep out of direct sunlight.

**SAFETY**

Use of **AV-100** is authorized by Avanti International only after completion of the required Safe Operating Practices Program (SOPP). Always use OSHA-approved personal protective equipment (PPE). Refer to the SDS for complete safety precautions. The SDS, mixing instructions, and Technical Manual are available by request or via download at [avantigrout.com](http://avantigrout.com).

**NOTICE**

The data, information and statements contained herein are believed to be reliable, but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. **NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE.** In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.